



POOL AND DECK COATINGS

Kelley Technical Coatings



Louisville, Kentucky 40201-3726
[502] 636-2561 [800] 458-2842
Fax [502] 635-5170 www.kelleytech.com

ALL OLYMPIC PRODUCTS ARE VOC COMPLIANT

Bulletin No. 119, pgs 1 of 3

The Application of (ZERON or POXOLON 2) or (PARALON 2 or OPTILON) on Previously Coated Pools

By following the recommendations listed in this Technical Bulletin, recoating your pool should produce excellent results. However, when these recommendation are not followed, future problems are being invited.

PLEASE NOTE: Existing surfaces with a rubber-based coating should be recoated only with a rubber-base coating. Likewise, epoxy coated surfaces should be recoated only with epoxy.

RECOATING RUBBER-BASED POOL SURFACES

First, test the existing finish for adhesion. If it does not come off with pressure from a putty knife or wire brush, then it should remain. If there is any loose coating, it should be removed and then those spots should be sanded with coarse sandpaper. If old rubber-based coating has a build-up of 6-8 coats, then we recommend removal of all coating by waterblasting or scraping if possible.

Secondly, the surface must be perfectly clean of oils and other contaminants. Wash thoroughly with No. 910 POOL WASHING COMPOUND or a tri-sodium phosphate (TSP) solution, particularly around the water line where these substances concentrate. Rinse with pressurized water.

If there are any bare concrete spots, they should be acid etched and neutralized and primed prior to coating.

The pool should be allowed to dry completely before coating.

NOTE: After 4 or 5 days of continuous rain, concrete and the adjacent soil become saturated. To allow the water to evaporate, the pool must dry for 3 or 4 days. If not, blistering is likely. Laying plastic on the surface will trap moisture and form condensation showing if surface is still damp.

RECOATING EPOXY COATED POOL SURFACES

Unlike rubber-based finishes, epoxy coatings do not build up. As a reaction to ultraviolet rays, epoxies eventually disappear. They should not be recoated until all gloss is gone and the finish is nearly transparent.

Before recoating, remove all residue such as suntan oil from the surface by washing with No. 910 POOL WASHING

COMPOUND or tri-sodium phosphate (TSP) solution. Then hose off. To remove stains and other contaminants, wash the pool again with a 10% solution of muriatic acid. After this, rewash the pool with tri-sodium phosphate (TSP). This is necessary to neutralize the acid. Both solutions are used because some contaminants can be removed only with acid while oil can only be removed with tri-sodium phosphate. Now hose off with clean water.

After this procedure is complete and the pool is dry, the pool may be recoated.

If, for some reason, a pool with an epoxy finish is to be recoated before all gloss has disappeared, the surface should be "scored" using coarse sandpaper. It should be scored in one direction. This gives the new coat a surface with which to achieve a satisfactory bond. Otherwise, the new epoxy coat does not have an adequate surface to adhere.

TIPS FOR RECOATING WITH EPOXY

(A) When there are bare spots, "spot prime" with GUNZITE PRIMER before coating.

(B) When using POXOLON 2 be sure to apply the second coat when the first is no longer tacky but before it cures.

(C) THOROUGHLY STIR IN THE CATALYST. We strongly recommend the use of an electric mixer to achieve proper mixing of any two-component material. All POXOLON 2 containers are only 3/4 full to leave room for the catalyst which is added at the ratio of one quart to each gallon and one gallon and one quart to each 5 gallon can. Catalyst for the 5 gallon can is under the lid. Catalyst for the gallon is in a separate container. CAUTION! All catalyst MUST be removed from the can containing the catalyst. It MUST BE THOROUGHLY mixed with the base. The induction period MUST be observed before application begins. If these important instructions are not observed, the POXOLON 2 or ZERON will remain soft and tacky.

(D) When mixing the base with the catalyst on residential and smaller pools, do not mix more than 2 one gallon containers at a time. This will prevent mixture from setting up before it is used. Five gallon containers set up faster and should only be used on larger pools where the materials are sprayed or being applied with larger paint rollers.

E) When rolling, do not use a longer nap cover than 7/16". Airless spraying provides the best job but requires an experienced spray operator. When using POXOLON 2 or ZERON pool coatings, the application equipment should be cleaned with No. 1109 SOLVENT immediately after using. Once it cures it is almost impossible to remove the coating.

F) Never apply POXOLON 2 or ZERON when the temperature is below 50°F. Below 50°F, they will not cure or harden. When there is a considerable drop in temperature at night, the following day the pool walls remain much colder than air temperature. The surface should be 50°F or above to achieve optimum results.

G) Avoid coating in the direct rays of the sun on real hot days. Coat on the shady side when the day is hot. Do not coat in the morning before the dew and condensation has had ample time to evaporate. Dry off the surface with rags or towels if dew or moisture is evident.

H) POXOLON 2 will cover 225 to 250 square ft. per gallon over other coatings. ZERON will cover 125 to 175 square feet per gallon. 12 mils of ZERON should be applied.

I) Always mix the coating in the center of the floor of the pool. Paint the pool walls first and the floor last. Paint the last section nearest the ladder where you will climb out. Wear soft soled shoes when painting. Never wear hard soled shoes.

J) POXOLON 2 or ZERON will produce a smooth, slick, non-porous finish which is easy to clean and keep clean. While the coating is still tacky, white silica sand should be lightly sifted on the bottom of wading pools, steps, and shallow areas. After the coating sets up, the excess sand should be brushed or vacuumed from the surface. Avoid using too much sand. A very light concentration will make the surface slip-proof.

PHYSICAL DATA

SOLVENTS:

No. 1108 for OPTILON and PARALON 2
No. 1109 for GUNZITE Primer, ZERON, POXOLON 2 and POXOFILL

FLASH POINT: For all of the above coatings and solvents exceed 105°F

MINIMUM RECOATING TIME OF GUNZITE, POXOPRIME II, POXOLON 2 AND ZERON:

4 hours @ 90°F to 95°F
6 hours @ 80°F to 85°F
5 hours @ 85°F to 90°F
8 hours @ 75°F to 80°F
Overnight below 75°F

OPTILON AND PARALON 2:

4 hours except in cool or damp weather; then allow overnight drying time:

MAXIMUM RECOATING TIME OF GUNZITE, POXOPRIME II, POXOLON 2 AND ZERON:

48 hours

POT LIFE:

POXOLON 2 AND GUNZITE PRIMER:

2 hours @ 90 F to 95°F
6 hours @ 68°F to 75°F
3 hours @ 85°F to 90°F
8 hours @ 60°F to 68°F
4 hours @ 75°F to 85°F

POXOPRIME II:

Approx. 2 hours @ 90°F
Approx. 4 hours @ 70°F

ZERON:

1/2 hour @ 85°F or above
1 hour @ 65°F to 85°F

NOTE: Above 85°F, use immediately after mixing thoroughly with catalyst. Do not mix 5 gallon containers unless you can use within 30 to 40 minutes. The smaller the quantity mixed at one time, the longer the pot life. ALWAYS MIX AND STORE IN A COOL PLACE.

NOTE: Pot life and working time can be increased by thinning 5% to 10% with No. 1109 SOLVENT. Highly recommended when surface temperature exceed 90°F. Add water with POXOPRIME II.

WARNING! Do not mix more of the 2 component epoxies than can be used during the pot life of the material.

CURING SCHEDULE: Before filling pool

POXOLON 2, ZERON and ZERON:

3 days @ 75°F and up
4 days @ 70°F to 75°F
5 days @ 65°F to 70°F
6 days @ 60°F to 65°F

PARALON : 5 days minimum

WAITING TIME FOR NEW CONCRETE TO "CURE" BEFORE APPLYING PARALON 2 AND OPTILON:

30 days - Minimum

DUST FREE DRYING TIME: all epoxy products

2 hours @ 80°F
1 hour @ 95°F
1 1/2 hours @ 85°F
2 hours @ 80°F
3 hours - below 70°F

SQUARE FEET PER GALLON:

POXOPRIME II:
Smooth Surface - 200 to 250
Porous or Textured - 175 to 225

GUNZITE PRIMER:
100 to 150 square feet per gallon

ZERON:
125 to 150 square feet per gallon

POXOLON 2:
225 to 250 - Over old epoxy

PARALON 2:
Spot Prime - Unthinned - 250 sq. ft. per gallon
Full Coat Refinishing - 250 sq. ft. per gallon

OPTILON:
250 to 300 sq. ft. per gallon



POOL AND DECK COATINGS

Kelley Technical Coatings



Louisville, Kentucky 40201-3726
[502] 636-2561 [800] 458-2842
Fax [502] 635-5170 www.kelleytech.com

ALL OLYMPIC PRODUCTS ARE VOC COMPLIANT

Bulletin No. 119, cont. pg 3 of 3

The Application of (ZERON or POXOLON 2) or (PARALON 2 or OPTILON) on Previously Coated Pools

CAN STABILITY:

All products - 2 years or over

AGEING PERIOD: After mixing and before application for: POXOPRIME II, GUNZITE, ZERON, and POXOLON 2 - See induction schedule on label.

APPLIED FILM THICKNESS:

GUNZITE: 8 to 10 mils
ZERON: 12 to 14 mils
PARALON 2: 2 to 4 mils
POXOPRIME II: 1/2 to 4 mils
POXOLON 2: 3 to 4 mils

CAUTION! - COMBUSTIBLE! Keep away from heat and open flame. Avoid prolonged contact with skin and breathing of vapor. Close container after each use. Areas of body or clothing on contact with uncured resin and/or catalyst should be thoroughly cleaned with solvent and washed with soap and water immediately. Use only where there is adequate ventilation. KEEP OUT OF THE REACH OF CHILDREN.

WARNING!

If you scrape or remove old paint, you may release lead dust. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at **1-800-424-LEAD** or log on to **www.epa.gov/lead**

Information herein given has been accumulated through many years of experience and verified by our technical personnel and is based upon tests believed to be reliable, but RESULTS ARE NOT GUARANTEED.

NOTE: KELLEY TECHNICAL COATINGS, INC. makes no implied warranty of merchantability, no implied warranty of fitness for a particular purpose and no other warranty, either express or implied, concerning its products.

KELLEY TECHNICAL COATINGS, INC.
Louisville, KY 40210